
5M Polar







QUALITY FEATURES

dispersion dyes DIN 54231

Anthracite G627

Material

Care labelling

Upholstery fabric category

The product complies with quality requirements according to DIN EN 14465:2006

Abrasion resistance EN ISO 12947-1 & 2	>50,000 cycles
Pilling EN ISO 12945-2 – 2000 cycles.	4-5
Light fastness EN ISO 105-B02 – method 2	4
Colour fastness to rubbing EN ISO 105-X12	4-5
Cigarette test DIN EN 1021-1	passed
MAK amines, azo dyes EN 14362-1 & 3	not detectable
Allergenic & carcinogenic	

Other test results are available on request from designwerk.

Coal G628

PROPERTIES OF THE COVER FABRIC

Discolouring due to cushions and/or clothing fabrics does not represent a defect of the upholstery fabric. Colour and texture deviations are typical for this product and do not entitle users to any claims. Interaction of pressure, heat and/or humidity may lead to pile displacement (pressure marks). This property is referred to as indentation or seating marks and is a typical feature that does not represent minor quality in any way.

Attention: Colour-contrasting seam only for approved models.



not detectable